# *In Situ* Analytical Electron Microscopy for Probing Nanoscale Electrochemistry

## by Ying Shirley Meng, Thomas McGilvray, Ming-Che Yang, Danijel Gostovic, Feng Wang, Dongli Zeng, Yimei Zhu, and Jason Graetz

and their tailored xides structures are at the heart of electrochemical energy storage technologies and advances in understanding and controlling the dynamic behaviors in the complex oxides, particularly at the interfaces, during electrochemical processes will catalyze creative design concepts for new materials with enhanced and better-understood properties. Such knowledge is not accessible without new analytical tools. New innovative experimental techniques are needed for understanding the chemistry and structure of the bulk and interfaces, more importantly how they change with electrochemical processes in situ.

Transmission Electron Analytical Microscopy (TEM) is used extensively to study electrode materials ex situ<sup>1-8</sup> and is one of the most powerful tools to obtain structural, morphological, and compositional information at nanometer scale by combining imaging, diffraction and spectroscopy, e.g., EDS (energy dispersive X-ray spectrometry) and Electron Energy Loss Spectrometry (EELS). Determining the composition/ structure evolution upon electrochemical cycling at the bulk and interfaces can be addressed by new electron microscopy technique with which one can observe, at the nanometer scale and in situ, the dynamic phenomena in the electrode materials. In electrochemical systems, for instance in a lithium ion battery (LIB), materials operate under conditions that are far from equilibrium, so that the materials studied ex situ may not capture the processes that occur in situ in a working battery. In situ electrochemical operation in the ultra-high vacuum column of a TEM has been pursued by two major strategies. In one strategy, a "nano-battery" can be fabricated from an all-solid-state thin film battery using a focused ion beam (FIB). The electrolyte is either polymer based or ceramic based without any liquid component. As shown in Fig. 1a, the interfaces between the active electrode material/electrolyte can be clearly observed with TÉM imaging, in contrast to the composite electrodes/electrolyte interfaces in conventional lithium ion batteries, depicted in Fig.1b, where quantitative interface characterization is extremely difficult if not impossible. A second strategy involves organic electrolyte, though this approach more closely resembles the actual operation conditions of a LIB, the extreme volatility

of the organic electrolytes present significant challenges for designing an *in situ* cell that is suitable for the vacuum environment of the TEM.

Significant progress has been made in the past few years on the development of in situ electron microscopy for probing nanoscale electrochemistry. In 2008, Brazier et al.<sup>9</sup> reported the first cross-section observation of an all solid-state lithium ion nano-battery by TEM. In this study the FIB was used to make a "nano-battery," from an all solid-state battery prepared by pulsed laser deposition (PLD). In situ TEM observations were not possible at that time due to several key challenges such as the lack of a suitable biasing sample holder and vacuum transfer of sample. In 2010, Yamamoto et al.<sup>10</sup> successfully observed changes of electric potential in an all-solid-state lithium ion battery in situ with electron holography (EH). The 2D potential distribution resulting from movement of lithium ions near the positive-electrode/electrolyte interface was quantified. More recently Huang et al. <sup>11</sup> and Wang et al.<sup>12,13</sup> reported the *in* situ observations of the electrochemical lithiation of a single SnO<sub>2</sub> nanowire electrode in two different *in situ* setups. In their approach, a vacuum compatible ionic liquid is used as the electrolyte, eliminating the need for complicated membrane sealing to prevent the evaporation of carbonate based organic electrolyte into the TEM column. One main limitation of this approach is that EELS spectral imaging is not possible due to the high plasmon signal of the ionic liquid.

To this end, we have developed a novel in situ instrumental system combining analytical electron microscopy with advanced spectroscopy to probe the dynamic phenomena in an all solid-state nano-battery. In situ electron microscopy is a versatile technique that yields insights into challenging questions that could not be obtained using other techniques. However, in order to fully exploit the capabilities, a very carefully thought-out plan of action is essential. It is important to recognize that this is not just a simple characterization tool, but a collection of tools that make up a complete experimental set-up: the choice of FIB operation conditions, specimen holder for biasing, grid materials and design as well as microscope environment must be thoroughly considered before performing an experiment. To ensure

beam transparency electron and minimize artifacts, the nano-battery must be thinned down to a thickness below 100 nm for quantitative analysis. In performing EELS, artifacts due to plural scattering have been an issue, particularly when the shallow Li K-edge is of interest. Radiation damage, through radiolysis or sputtering, has been a big concern in studying Licontaining materials. Some strategies on reducing undesirable plural scattering and radiation damage have been developed for this project; generally operating TEM at a higher voltage (i.e., 300 kV) can be beneficial.<sup>14</sup> One of the key issues for observing and studying electrochemical reactions in situ under TEM is to assure that the very thin cross section samples (nano-batteries) are still electrochemically functional after the FIB fabrication. Other important barriers that we have overcome include (i) solidstate nano-battery fabrication and *in situ* monitoring of electrochemistry functionality; (ii) custom designed TEM sample grids that enable robust electric contacts and electrochemical testing; and (iii) coupled imaging, diffraction, and spectroscopy for comprehensive structural and chemical analysis of nanobatteries under biasing; particularly tracking the Li may be possible by developed Li K-edge spectroscopy and mapping.

## All Solid State Nano FIB Fabrication

Pulsed laser deposition (PLD) is capable of producing thin-films of lithium transition metal oxides with dense and smooth morphology. Various PLD films can be arranged in a multi-layer structure to form a complete all-solidstate battery. Fig. 1a shows an example with the following configuration: Au (current collector) / SnO<sub>2</sub> (anode) /  $Li_{3,4}V_{0,6}Si_{0,4}O_4$  (electrolyte) / LiCoO<sub>2</sub> (cathode) / Pt (current collector). PLD has been widely recognized as a very promising, versatile and efficient technique for the growth of high quality films from a variety of materials even containing volatile components with complex stoichiometries. By carefully controlling the laser energy, targetsubstrate distance and angle, substrate temperature and the atmosphere in the PLD chamber, one can not only deposit films with accurate stoichiometry,

**Meng**, *et al*. (continued from previous page)



Fig. 1. TEM micrograph of a FIB prepared nanoscale all-solid-state lithium ion cell and SEM micrograph of a conventional lithium ion cell.

but also control the crystallographic orientation of the films, if they are crystalline. In our nano-battery, the electrodes are crystalline materials while the lithium vanadium silicon oxide (LVSO) is amorphous with a reported 10-3-10-4S/cm<sup>2</sup>.15 ionic conductivity More importantly, the PLD grown films are much denser than films prepared by other deposition techniques such as sputtering, and are therefore well suited for FIB processing (porous films are difficult to handle with the focused ion beam).

The nano-battery was fabricated by first preparing a cross section sample (from a solid-state battery) and cutting it down to a micron-sized battery (about a few micrometers thick) using a focused ion beam in a dual beam SEM equipped with a micromanipulator. As shown in Fig. 2, the electrochemical measurements were conducted throughout the FIB preparation process to monitor the status of the battery. In Fig. 2b, we applied constant current charging mode on an isolated cross section trench with 1nA (current density about 0.5mA/cm<sup>2</sup>). The voltage rises and shows a plateau at 3.4 V, indicating the de-intercalation of Li from LiCoO<sub>2</sub>. The reversible capacity is observed upon discharging with 1nA though it is clear that polarization in this particular nano-battery is high. The in situ monitoring of the status of the nano-battery is critical to ensure the electrochemical functionality of the nano-battery remains intact throughout FIB processing. Ion beam damage of the active components and possible shorting of the battery can be prevented by optimizing the FIB operating conditions.



Fig. 2. Electrochemical activity of the all-solid-state battery can be preserved during FIB process. The electrochemical response is from the isolated trench shown in the SEM micrograph.

## Biasing Setup for NanoElectrochemisty

To ensure good electric contacts between the TEM holder and sample grid, extra care has to be taken to make sure the sample biasing setup is repeatable and robust. As shown in Fig. 3, our custom designed TEM grids (by TEMwindows) have an insulating TEMwindow (made of SiN), which holds an electron transparent cross-section of an electrochemical device (i.e., solid state battery). Two gold pads deposited on a Si frame with a 40 µm opening gap provide electronic contacts for both electrodes. It should be noted that in order to prevent shorting between the electrodes, additional milling steps need to be taken to isolate the cathode and anode when establishing the contacts on Au pads, as depicted in Fig. 3.

This setup ensures the solid-state battery cross section area can be accessed by the electron beam while the mechanical stability of the sample on the grid is well maintained. Fig. 3a shows a graphic representation of the entire sample on the grid, which has been transported from one microscope to another. The mechanical stability of the sample on the grid is essential since the cross section has to be further thinned down (from 2000 nm to <100 nm) to enable quantitative EELS characterization. It should also be pointed out that solid electrolytes such as LVSO or polymer electrolytes such as LiPON are sensitive to moisture (though to a lesser extent compared with a carbonate based organic electrolyte), air exposure of the nano-battery must be minimized or eliminated.

## In Situ TEM Observations

A nano-battery cross section of lithium nickel manganese oxides with a LVSO electrolyte was analyzed in a JEOL 3000F TEM equipped with a Gatan image filter (GIF). One of the typical cross-section TEM images of the nano-batteries is given in Fig. 4a, showing all of the components. The LVSO electrolyte layer is amorphous as confirmed by electron diffraction from the area, giving diffuse rings typical of amorphous phase structure. Below the LVSO electrolyte is the crystalline lithium nickel manganese oxide cathode, where crystallites in random orientations may be distinctly seen. Under the cathode there is an interfacial phase that appears to have epitaxially grown into the SiO, film below it. At the bottom of the image we see the silicon bulk substrate. Lithium and transitional metal elements were mapped using EELS, for direct visualization of their distribution in the electrolyte and electrode. Fig. 4b shows the nickel, vanadium, and lithium distributions, indicating that nickel is not evenly distributed but highly concentrated in some particles, and vanadium is evenly distributed throughout the electrolyte phase. One can clearly see that transition metal oxide electrode is indeed the lithium source. Fig. 4c displays the lithium intensity, which was highest in the center of the electrode region. The interface between the electrode and the current collector is atomically flat while the interface between the electrode and electrolyte is relatively rough (tens of nm). A more thorough examination by SEM/EDX of the entire nano-battery shows little or no Ga signal, indicating that unwanted ion implantation can be minimized during the FIB preparation.

The completed nano-battery has extremely small dimensions (about 10  $\mu$ m × 30  $\mu$ m × 100 nm), which present another set of challenges for in situ TEM. The suitable current range for such a functional nano-battery should be in the range of a few pA (10<sup>-12</sup> A). If a 100 nA current is applied to such a nano battery, the actual current density is equivalent of 2 to 3A/cm<sup>2</sup> (a typical LIB operates at a few or tens of mA/cm<sup>2</sup>), the battery will fail catastrophically. Figure 5, shows the results from one of the first trials of biasing a nano-battery with 100 nA current in situ. The battery "exploded" inside the TEM column—the current collector (Pt), electrode, and electrolyte were completely smeared and platinum (the current collector) was deposited throughout the cross sectional area. With the recent advancement in nano metrology, it is now possible to probe nano devices with fA accuracy.

#### **Concluding Remarks**

Understanding and controlling the interfaces in energy systems is identified as one of the Grand Challenges of Science by the Basic Energy Sciences Advisory Committee (BESAC).<sup>16</sup> The development of our new in situ analytical electron microscopy is in response to this dedicated and coordinated effort to invent, design, and employ novel and sophisticated analytical systems underpinning of the challenge. We believe that the in situ analytical electron microscopy for probing nanoscale electrochemistry will enable us to understand dynamic changes-particularly those that happen

<sup>(</sup>continued on next page)



Fig. 3. In situ biasing setup of a lithium ion cell on a custom-designed TEM grid. The thickness of the battery is in the order of 100 nm.

**Meng**, *et al*. (continued from previous page)



FIG. 4. The unique capability of analytical transmission electron microscopy, combining imaging and chemical analysis with high spatial resolution.

at the interfaces during the active operation of electrochemical cells—and ultimately learn to control the dynamic phenomena for design and develop the next generation of materials for energy storage.

#### **Acknowledgments**

This research is conducted through the support by the Northeastern Center for Chemical Energy Storage, an Energy Frontier Research Center funded by the U.S. Department of Energy, Office of Basic Energy Sciences, under award number DE-SC0001294. Y.S. Meng also acknowledges funding support for the development of all-solid-state lithium ion battery and TEM *in situ* cell and grid by the single investigator grant by the U.S. Department of Energy, Office of Basic Energy Sciences, under award number DE-SC0002357.

## **About the Authors**

YING SHIRLEY MENG received her BS degree (with first class honors) in materials science and engineering from Nanyang Technological University of Singapore in 2000 and her PhD in advanced micro- and nano systems from Singapore-MIT Alliance (SMA) in 2005. She won the Materials Research Society (MRS) Graduate Student Award in 2003 for her pioneering work on designing new high energy electrode materials for lithium ion batteries from first principles. In 2008, she joined one of the top ten materials science and engineering departments in USA at University of Florida. Dr. Meng later joined University of California San Diego and become the group leader of the Laboratory for Energy Storage and Conversion (LESC). Dr. Meng recently received the prestigious National Science Foundation (NSF) CAREER award. She may be reached at shirleymeng@ucsd. edu.

THOMAS MCGILVRAY received his bachelor's degree (cum laude) in mechanical engineering from the Florida, Gainesville, University of Florida, USA, in 2010. He is currently working toward his PhD in materials science at the University of California, San Diego, USA. He is a graduate student researcher for the Laboratory for Energy Storage and Conversion (LESC) under PI Shirley Meng. His current research includes in situ transmission electron microscopy and atom probe tomography of lithium ion battery materials with a concentration on focused ion beam sample preparation. He may be reached at tmcgilvr@ucsd.edu.

MING-CHE YANG graduated from the National Tsing Hua Universit y, Hsinchu, Taiwan with a master's degree in materials science and engineering in 2001. He has worked at National Nano Device Laboratory, Hsinchu, Taiwan for 5 years as an assistant researcher. He is currently a PhD candidate in materials science and engineering at the University of Florida. He has worked withShirley Meng at UF since 2008 on developing novel electrode of li-lon batteries. Now his research interests are high-voltage spinel materials, nanosized anode materials, and all-solid state thin film Li- ion batteries. He maybe reached at myang@ufl.edu.

**DANIJEL GOSTOVIC** received his bachelor's degree in materials science and engineering from Northwestern University in 2004 and his PhD in materials science and engineering from the University of Florida in 2009. Dr. Gostovic contributed to the project on the FIB processing of the nano batteries and *in situ* biasing setup in TEM while he worked as a postdoc fellow at the LESC group in UCSD. He may be reached at gostofish@gmail.com.

**Feng Wang** is a research associate from Brookhaven National Laboratory. He received his PhD in condensed matter physics from the University of Alberta in 2007. He was the recipient of Izaak Walton Killam Memorial Scholarship in 2004, the Microscopy Society of America Presidential Student Awards in 2006, and the NSERC PDF fellowship in 2009. He currently focuses his research on electron microscopy and spectroscopy of electrode materials for Li-ion batteries. He may be reached at fwang@bnl.gov.

**DONGLI ZENG** is currently a process engineer at Applied Materials in Santa Clara, CA. Her research interests are in the area of electrode materials for lithium ion batteries. As a postdoctoral research associate in the Sustainable Energy Technologies Department at Brookhaven National Laboratory, she was developing nanoscale lithium battery fabrication techniques. Zeng received her BS and MS degrees from Peking University in China and her PhD degree from State University of New York at Stony Brook in U.S. She may be reached at dongli.zeng@gmail.com.



Fig. 5. Effect of high current density (in the order of 2500 mA/cm<sup>2</sup>) on the all solid state lithium ion cell.

YIMEI ZHU is a Senior Physicist and Group Leader in the Department of Condensed Matter Physics, and a co-founder of the Center for Functional Nanomaterials, Brookhaven National Laboratory. He is also an adjunct professor in the Department of Applied Physics and Mathematics, Columbia University, and the Department of Physics and Astronomy at Stony Brook University. His research interests include advanced electron microscopy and nanostructured energy materials. Zhu has published over 300 peer-reviewed journal articles. During his career, he has served on various academic committees and has received many honors. Zhu received his PhD from Nagoya University, Japan. He is an elected Fellow of the Microscopy Society of America and American Physical Society. He may be reached at zhu@bnl.gov.

**JASON GRAFTZ** received his PhD in materials science from the California Institute of Technology in 2003 and is a currently a staff scientist and Energy Storage Group Leader at Brookhaven National Laboratory. He is a U.S. Expert of the International Energy Agency on hydrogen storage and was the recipient of the 2006 Ewald Wicke Award for his work on metal hydrides along with the Presidential Early Career Award for Young Scientists and Engineers (PECASE) in 2008. He may be reached at graetz@bnl.gov.

#### References

- L. Dupont, M. Hervieu, G. Rousse, C. Masquelier, M. R. Palacin, Y. Chabre, and J. M. Tarascon, TEM studies: J. Solid State Chem., 155, 394 (2000).
- 2. H. Gabrisch, R. Yazami, and B. Fultz, J. Power Sources, **119**, 674 (2003).
- J. Graetz, C. C. Ahn, R. Yazami, and B. Fultz, *J. Phys. Chem. B*, **107**, 2887 (2003).
- J. Graetz, C. C. Ahn, H. Ouyang, P. Rez, and B. Fultz, *Phys. Rev. B*, **69**, 235103-1 (2004).
- Y. S. Meng, G. Ceder, C. P. Grey, W. S. Yoon, and Y. Shao-Horn, *Electrochem. Solid-State Lett.*, 7, A155 (2004).
- Y. S. Meng, G. Ceder, C. P. Grey, W. S. Yoon, M. Jiang, J. Breger, and Y. Shao-Horn, *Chem. Mater.*, **17**, 2386 (2005).
- H. Gabrisch, J. D. Wilcox, and M. M. Doeff, *Electrochem. Solid-State Lett.*, 9, A360 (2006).
- 8. H. Gabrisch, J. Wilcox, and M. M. Doeff, *Electrochem. Solid-State Lett.*, **11**, A25 (2008).
- A. Brazier, L. Dupont, L. Dantras-Laffont, N. Kuwata, J. Kawamura, and J. M. Tarascon, *Chem. Mater.*, 20, 2352 (2008).
- K. Yamamoto, Y. Iriyama, T. Asaka, T. Hirayama, H. Fujita, C. A. J. Fisher, K. Nonaka, Y. Sugita, and Z. Ogumi, Angewandte Chem.-Int'l. Ed., 49, 4414 (2010).

- J. Y. Huang, L. Zhong, C. M. Wang, J. P. Sullivan, W. Xu, L. Q. Zhang, S. X. Mao, N. S. Hudak, X. H. Liu, A. Subramanian, H. Y. Fan, L. A. Qi, A. Kushima, and J. Li, *Science*, **330**, 1515 (2010).
- C. M. Wang, W. Xu, J. Liu, D. W. Choi, B. Arey, L. V. Saraf, J. G. Zhang, and Z. G. Yang, *J. Mater. Res.*, 25, 1541 (2010).
- 13. C. M. Wang, W. Xu, J. Liu,J. G. Zhang, L. V. Saraf, B. W. Arey, D. Choi, Z. G. Yang, and J. Xiao, *Nano Letters, ASAP online (2011).*
- F. Wang, J. Graetz, M. S. Moreno, C. Ma, L. J. Wu, V. Volkov, and Y. M. Zhu, *ACS Nano*, 5, 1190 (2011).
  N. Kuwata, J. Kawamura, K.
- N. Kuwata, J. Kawamura, K. Toribami, T. Hattori, and N. Sata, *Electrochem. Commun.*, 6, 417 (2004).
- 16. BESAC Directing Matter and Energy: Five Challenges for Science and the Imagination, Department of Energy, Office of Basic Energy Sciences (2008).